

Powder paint (for interior application)

Guide Formulation

Ingredients	Parts by weight	By percent
Emulsion powder	127,0	12,7%
KimaCell Cellulose ether	5,0	0,5%
Cellulose fibre	80,0	8,0%
Film forming agent	19,0	1,9%
Defoamer	4,0	0,4%
Dispersant,phosphate	2,5	0,3%
Talc, 0 5 µm	230,0	23,0%
Calcite, 0 0,9 um	200,0	20,0%
Calcite, 0 2,5 µm	130,0	13,0%
Calcite, 0 1 um	100,0	10,0%
Titanium dioxide	100,0	10,0%
Lime hydrate	2,5	0,3%
	1.000,0	100,00%